

IMAPUR 1882/25

DESCRIPTION Aliphatic one-component PU resin. Polyester based. In solvent mixture.
Dry touch. Stiff hand. Excellent lightfastness. High temperature resistance. Good hydrolysis resistance.

USE Skin or topskin for PU articles. It can be used in mix with resins of the same nature after verifying compatibility.

Characteristics of the product	<i>Aspect:</i>	Viscous liquid
	<i>Dry Content:</i>	25,00± 1%
	<i>Solvent/s</i>	IBA/DEC
	<i>Viscosity 25 °C:</i>	15.000 - 30.000 mPa.s

Physical characteristics of the dry film	<i>Modulus 100% (Kg/cm2):</i>	220
	<i>Tensile Stenght(Kg/cm2):</i>	380
	<i>Elongation(%):</i>	210
	<i>Kofler (T.ramm °C):</i>	200
	<i>Kofler (Melting °C):</i>	220

Modifiers	<i>For the pigmentation</i>	NOVA TC ND
	<i>For the colouring</i>	IMACOLOR
	<i>To improve the spreading</i>	IMASIL S 100

Packing	<i>Metal drums of Kgs:</i>	180
----------------	----------------------------	-----

Storage The product must be stored at temperatures between -1 °C and 30 °C.
In this conditions the product is stable for 6 months

Notes KEEP PACKINGS PERFECTLY SEALED

Legend	N.A. = NOT APPLIABLE	N.D. = NON DETERMINED	F.C. = FORD CUP		
<i>First issuing date:</i>	15/02/2021	<i>Revision date:</i>	<i>Revision nr.:</i>	<i>Print date:</i>	30/09/2021
