

IMAPUR 2400 HT

DESCRIPTION Aromatic one-component skin. One-solvent. Soft.
 Polyester-based polyurethane. High melting temperature.

USE It can be used in different fields when soft hand and high temperature resistance are required.

Characteristics of the product	<i>Aspect:</i>	Viscous liquid
	<i>Dry Content:</i>	35,00%± 1
	<i>Solvent/s</i>	DMF
	<i>Viscosity:</i>	50.000 - 80.000 mPa.s

Physical characteristics of the dry film	<i>Modulus 100% (Kg/cm2):</i>	40
	<i>Modulus 300% (Kg/cm2):</i>	120
	<i>Tensile Stenght(Kg/cm2):</i>	500
	<i>Elongation(%):</i>	600
	<i>T.Kofler (softening) (°C):</i>	200
	<i>T.Kofler (melting point)(°C):</i>	210

Modifiers	<i>For dilution</i>	DMF, DMF/TOL (MIX)
	<i>For the pigmentation</i>	NOVA TC ND
	<i>For the colouring</i>	IMACOLOR
	<i>To improve the spreading</i>	IMASI 20

Packing	<i>Metal drums of Kgs:</i>	200
----------------	----------------------------	-----

Storage The product must be stored at temperatures between -1 °C and 30 °C. In this conditions the product is stable for 6 months

Notes SHELTER FROM MOISTURE
 KEEP PACKINGS PERFECTLY SEALED

Legend	N.A. = NOT APPLIABLE	N.D. = NON DETERMINED	F.C. = FORD CUP
<i>First issuing date:</i>	22/12/2009	<i>Revision date:</i>	21/09/2016
		<i>Revision nr.:</i>	6
		<i>Print date:</i>	26/02/2020