

IMAPUR 2900

DESCRIPTION

Aromatic one-component top-skin. One-solvent. Stiff.
Outstanding temperature resistance.

USE

Product indicated as top-skin both for PVC and polyurethane. As the adhesion is strictly correlated to the quantity of plasticizer in PVC, it is a good rule to do preliminary tests.

Characteristics of the product

<i>Aspect:</i>	Viscous liquid
<i>Dry Content:</i>	35,00± 1%
<i>Solvent/s</i>	DMF
<i>Viscosity:</i>	80.000 - 120.000 mPa.s

Physical characteristics of the dry film

<i>Modulus 100% (Kg/cm2):</i>	130
<i>Modulus 300% (Kg/cm2):</i>	435
<i>Tensile Stenght(Kg/cm2):</i>	550
<i>Elongation(%):</i>	370
<i>Kofler (T.ramm °C):</i>	220
<i>Kofler (Melting °C):</i>	230

Modifiers

<i>For dilution</i>	DMF, DMF/TOL (MIX)
<i>For the pigmentation</i>	NOVA TC ND
<i>For the colouring</i>	IMACOLOR
<i>To improve the spreading</i>	IMASI 20

Packing

<i>Metal drums of Kgs:</i>	200
----------------------------	-----

Storage

The product must be stored at temperatures between -1 °C and 30 °C.
In this conditions the product is stable for 6 months

Notes

KEEP PACKINGS PERFECTLY SEALED
SHELTER FROM MOISTURE

Legend	N.A. = NOT APPLIABLE	N.D. = NON DETERMINED	F.C. = FORD CUP				
<i>First issuing date:</i>	19/04/2000	<i>Revision date:</i>	04/11/2014	<i>Revision nr.:</i>	6	<i>Print date:</i>	03/03/2017
