

IMAPUR 5134 PCD-3

DESCRIPTION

Aromatic one-component adhesive. In solvent mixture.
Polycarbonate based polyurethane. High hydrolysis resistance.

USE

The product shall be used when a soft hand and hydrolysis resistance are required.

Characteristics of the product

<i>Aspect:</i>	Viscous liquid
<i>Dry Content:</i>	40,00± 1%
<i>Solvent/s</i>	DMF/TOL
<i>Viscosity:</i>	40.000 - 60.000 mPa.s

Modifiers

<i>For the cross-linking</i>	IMACAT 75,IMACAT 76B,IMACAT BM+IMACID BV
<i>For dilution</i>	DMF, TOL, MEK, AE
<i>For the pigmentation</i>	NOVA TC ND
<i>For the colouring</i>	IMACOLOR

Packing

Metal drums of Kgs: 200

Storage

The product must be stored at temperatures between -1 °C and 30 °C.
In this conditions the product is stable for 6 months

Notes

KEEP PACKINGS PERFECTLY SEALED
SHELTER FROM MOISTURE

Legend	N.A. = NOT APPLIABLE	N.D. = NON DETERMINED	F.C. = FORD CUP		
<i>First issuing date:</i>	30/08/2016	<i>Revision date:</i>	<i>Revision nr.:</i>	<i>Print date:</i>	06/03/2017
