

DESCRIPTION Aromatic one-component adhesive. In solvent mixture. Very soft. Polyether-based polyurethane. High hydrolysis resistance.

USE The product shall be used when a very soft hand and hydrolysis resistance are required.

Characteristics of the product	<i>Aspect:</i>	Viscous liquid
	<i>Dry Content:</i>	40,00%± 1
	<i>Solvent/s</i>	DMF/TOL
	<i>Viscosity:</i>	40.000 - 60.000 mPa.s

Physical characteristics of the dry film	<i>Modulus 100% (Kg/cm2):</i>	15
	<i>Modulus 300% (Kg/cm2):</i>	35
	<i>Tensile Stenght(Kg/cm2):</i>	105
	<i>Elongation(%):</i>	890
	<i>T.Kofler (softening) (°C):</i>	160
	<i>T.Kofler (melting point)(°C):</i>	170

Modifiers	<i>For the cross-linking</i>	IMACAT 75,IMACAT 76B,IMACAT BM+IMACID BV
	<i>For dilution</i>	DMF, TOL, MEK, AE
	<i>For the pigmentation</i>	NOVA TC ND
	<i>For the colouring</i>	IMACOLOR

Packing	<i>Metal drums of Kgs:</i>	200
----------------	----------------------------	-----

Storage The product must be stored at temperatures between 10 °C and 30 °C. In this conditions the product is stable for 6 months

Notes KEEP PACKINGS PERFECTLY SEALED
 SHELTER FROM MOISTURE

Legend	N.A. = NOT APPLIABLE	N.D. = NON DETERMINED	F.C. = FORD CUP
<i>First issuing date:</i>	19/04/2000	<i>Revision date:</i>	04/12/2018
		<i>Revision nr.:</i>	5
		<i>Print date:</i>	26/02/2020