

IMAPUR G 73

DESCRIPTION

Aromatic one-component PU resin. Polyester based. One solvent.
Medium-soft. Good washing resistance.

USE

Thermoadhesive applicable during dry process, the product can be reactivated at 140-160°C.
It can be used for OCS lamination.

Characteristics of the product

<i>Aspect:</i>	Viscous liquid
<i>Dry Content:</i>	45,00%± 1
<i>Solvent/s</i>	DMF
<i>Viscosity (25 °C)</i>	20.000 - 40.000 mPa.s

Physical characteristics of the dry film

<i>Modulus 100% (Kg/cm2):</i>	40
<i>Modulus 300% (Kg/cm2):</i>	70
<i>Tensile Stenght(Kg/cm2):</i>	200
<i>Elongation(%):</i>	580
<i>T.Kofler (softening) (°C):</i>	116
<i>T.Kofler (melting point)(°C):</i>	126

Packing

<i>Metal drums of Kgs:</i>	200
----------------------------	-----

Storage

The product must be stored at temperatures between 5 °C and 30 °C. In these conditions the product is stable for 6 months

Notes

KEEP PACKINGS PERFECTLY SEALED
SHELTER FROM MOISTURE
STIR BEFORE USE

Legend	N.A. = NOT APPLIABLE	N.D. = NON DETERMINED	F.C. = FORD CUP				
<i>First issuing date:</i>	26/10/2005	<i>Revision date:</i>	26/02/2021	<i>Revision nr.:</i>	9	<i>Print date:</i>	07/12/2021
