

IMAPUR HS 282

DESCRIPTION

Aromatic High-solid. Solvent-free. Very soft.
Good hydrolysis resistance. MEKO - FREE.

USE

Solvent-free polyurethane, used for both compact and expanded soft films.
The product has to be cross-linked with IMACAT 09 (15,1 phr) or with IMACAT 08 (8,1 phr) or IMACAT 09 VF (14,2 phr).

Characteristics of the product

<i>Aspect:</i>	Viscous liquid
<i>Dry Content:</i>	100,00
<i>Solvent/s</i>	NA
<i>Viscosity:</i>	30.000 - 60.000 mPa.s

Modifiers

<i>For the cross-linking</i>	IMACAT 09, IMACAT 08, IMACAT 09 VF
<i>To improve the spreading</i>	IMASIL S 101

Packing

<i>Metal drums of Kgs:</i>	200
----------------------------	-----

Storage

The product must be stored at temperatures between -1 °C and 30 °C. In these conditions the product is stable for 6 months

Notes

KEEP PACKINGS PERFECTLY SEALED

Legend	N.A. = NOT APPLICABLE	N.D. = NON DETERMINED	F.C. = FORD CUP				
<i>First issuing date:</i>	03/08/2017	<i>Revision date:</i>	03/08/2017	<i>Revision nr.:</i>		<i>Print date:</i>	28/08/2017
