

IMAPUR HS 286 G

DESCRIPTION	Aromatic High-solid. Solvent-free. Very soft. Good hydrolysis resistance.MEKO - FREE.Embossable.	
USE	Solvent-free polyurethane, used for both compact and expanded soft films. The product has to be cross-linked with IMACAT 089 (13 phr).	
Characteristics of the product	<i>Aspect:</i>	Viscous liquid
	<i>Dry Content:</i>	100,00
	<i>Solvent/s</i>	NA
	<i>Viscosity:</i>	20.000 - 50.000 mPa.s
Physical characteristics of the dry film	<i>Modulus 100% (Kg/cm2):</i>	15
	<i>Modulus 300% (Kg/cm2):</i>	30
	<i>Tensile Stenght(Kg/cm2):</i>	40
	<i>Elongation(%):</i>	525
	<i>Kofler (T.ramm °C):</i>	170
	<i>Kofler (Melting °C):</i>	210
Modifiers	<i>For the cross-linking</i>	IMACAT 089
	<i>For the pigmentation</i>	NOVA W SERIE
	<i>To improve the spreading</i>	IMASIL S 101, IMASIL S 103
Packing	<i>Metal drums of Kgs:</i>	210
Storage	The product must be stored at temperatures between -1 °C and 30 °C. In this conditions the product is stable for 6 months	
Notes	KEEP PACKINGS PERFECTLY SEALED	

Legend	N.A. = NOT APPLIABLE	N.D. = NON DETERMINED	F.C. = FORD CUP				
<i>First issuing date:</i>	05/10/2018	<i>Revision date:</i>	18/03/2019	<i>Revision nr.:</i>	1	<i>Print date:</i>	22/05/2019
