

Sede Legale: 27036 MORTARA (Pavia) IT via E.SEGRE' 23 Tel. 0384 297311 Fax 0384 296732 - E-mail info@imadelta.com

## **IMATHANE CS 11**

**DESCRIPTION** Aromatic one-component. Chips. Medium soft.

**USE** Product to be used, after dissolution in DMF at the wished concentration, as

general purpose skin.

For dissolution use DMF and DMF mixtures and other solvents

Chips

N.A.

100,00

in which DMF represents at least the 80%

**Characteristics of** 

the product

Aspect:
Dry Content:
Solvent/s

Viscosity: 10.000 - 20.000 mPa.s (25% in DMF)

Physical characteristics

of the dry film

 Modulus 100% (Kg/cm2):
 50

 Modulus 300% (Kg/cm2):
 95

 Tensile Stenght(Kg/cm2):
 450

 Elongation(%):
 600

 Kofler (Melting °C):
 170

Modifiers For dilution DMF, DMF/TOL (MIX)

For the pigmentation NOVA TC ND
For the colouring IMACOLOR
To improve the spreading IMASI 20

Packing Bags of Kgs: 25

Storage The product must be stored at temperatures between -1 °C and 30 °C.

In this conditions the product is stable for 6 months

Notes KEEP PACKINGS PERFECTLY SEALED

SHELTER FROM MOISTURE

Legend	N.A. = NOT APF	PLIABLE N.C	). = NON DETERMINED	F.C. = FORD CUP			
First issuing date:	20/04/2000	Revision date	e: 09/04/2015	Revision nr.:	1	Print date:	02/04/2019