

IMATHANE CS 14

DESCRIPTION	Aromatic one-component skin. Chips. Medium-stiff.	
USE	Product to be used, after dissolution in DMF at the wished concentration, as general purpose skin. For dissolution use DMF and DMF mixtures and other solvents in which DMF represents at least the 80%	
Characteristics of the product	<i>Aspect:</i>	Chips
	<i>Dry Content:</i>	100,00
	<i>Solvent/s</i>	N.A.
	<i>Viscosity:</i>	10.000 - 20.000 mPa.s (25% in DMF)
Physical characteristics of the dry film	<i>Modulus 100% (Kg/cm2):</i>	80
	<i>Modulus 300% (Kg/cm2):</i>	130
	<i>Tensile Strength (Kg/cm2):</i>	400
	<i>Elongation(%):</i>	700
	<i>Kofler (Melting °C):</i>	180
Modifiers	<i>For dilution</i>	DMF, DMF/TOL (MIX)
	<i>For the pigmentation</i>	NOVA TC ND
	<i>For the colouring</i>	IMACOLOR
	<i>To improve the spreading</i>	IMASI 20
Packing	<i>Bags of Kgs:</i>	25
Storage	The product must be stored at temperatures between -1 °C and 30 °C. In this conditions the product is stable for 6 months	
Notes	KEEP PACKINGS PERFECTLY SEALED SHELTER FROM MOISTURE	

Legend	N.A. = NOT APPLIABLE	N.D. = NON DETERMINED	F.C. = FORD CUP
<i>First issuing date:</i>	20/04/2000	<i>Revision date:</i>	09/04/2015
		<i>Revision nr.:</i>	1
		<i>Print date:</i>	02/04/2019