

## IMATHANE CS 19

<b>DESCRIPTION</b>	Aromatic one-component. Chips. Stiff.	
<b>USE</b>	Product to be used, after dissolution in DMF, as stiff skin. It has to be used in coating or as a lacquer to be applied by printing roll.	
<b>Characteristics of the product</b>	<i>Aspect:</i>	Chips
	<i>Dry Content:</i>	100,00
	<i>Solvent/s</i>	N.A.
	<i>Viscosity:</i>	10.000 - 20.000 mPa.s (25% in DMF)
<b>Physical characteristics of the dry film</b>	<i>Modulus 100% (Kg/cm2):</i>	200
	<i>Modulus 300% (Kg/cm2):</i>	310
	<i>Tensile Stenght(Kg/cm2):</i>	450
	<i>Elongation(%):</i>	550
	<i>Durezza Shore("A"):</i>	67 D
	<i>Kofler (Melting °C):</i>	210
<b>Modifiers</b>	<i>For dilution</i>	DMF,DMF/MEK (MIX)
	<i>For the pigmentation</i>	NOVA TC ND
	<i>For the colouring</i>	IMACOLOR
	<i>To improve the spreading</i>	IMASI 20
<b>Packing</b>	<i>Bags of Kgs:</i>	25
<b>Storage</b>	The product must be stored at temperatures between -1 °C and 30 °C. In this conditions the product is stable for 6 months	
<b>Notes</b>	SHELTER FROM MOISTURE KEEP PACKINGS PERFECTLY SEALED	

---

<b>Legend</b>	N.A. = NOT APPLIABLE	N.D. = NON DETERMINED	F.C. = FORD CUP				
<i>First issuing date:</i>	19/04/2000	<i>Revision date:</i>	03/04/2018	<i>Revision nr.:</i>	2	<i>Print date:</i>	02/04/2019

---