

## IMATHANE CS 64 PC

<b>DESCRIPTION</b>	Aromatic one-component skin. Chips. Polycarbonate-based polyurethane.	
<b>USE</b>	The product can be used as a skin with good hydrolysis stability, after dissolution with DMF or DMF/TOL at the wished concentration. If DMF/TOL is used, DMF has to represent at least the 80%.	
<b>Characteristics of the product</b>	<i>Aspect:</i>	Chips
	<i>Dry Content:</i>	100,00
	<i>Solvent/s</i>	N.A.
	<i>Viscosity:</i>	7.000 - 11.000 mPa.s (25% in DMF)
<b>Physical characteristics of the dry film</b>	<i>Modulus 100% (Kg/cm2):</i>	70
	<i>Modulus 300% (Kg/cm2):</i>	130
	<i>Tensile Strength(Kg/cm2):</i>	450
	<i>Elongation(%):</i>	600
	<i>Durezza Shore("A"):</i>	88 A
<b>Modifiers</b>	<i>For dilution</i>	DMF, MISCELA DMF/TOL
	<i>For the pigmentation</i>	NOVA TC ND
	<i>For the colouring</i>	IMACOLOR
	<i>To improve the spreading</i>	IMASI 20
<b>Packing</b>	<i>Bags of Kgs:</i>	25
<b>Notes</b>	KEEP PACKINGS PERFECTLY SEALED SHELTER FROM MOISTURE	

<b>Legend</b>	N.A. = NOT APPLIABLE	N.D. = NON DETERMINED	F.C. = FORD CUP
<i>First issuing date:</i>	20/09/2013	<i>Revision date:</i>	02/12/2016
		<i>Revision nr.:</i>	2
		<i>Print date:</i>	13/03/2017