



升华集团德清华源颜料有限公司  
SHENGHUA GROUP DEQING HUAYUAN  
PIGMENT CO., LTD.



## TECHNICAL DATA

Edition of: 2010-12-8

<b>Trade name</b>	Iron oxide brown			
<b>Type</b>	686			
<b>REACH</b>	Registration No. 01-2119457614-35-0043, 01-2119457554-33-0014, 01-2119457646-28-0014			
<b>Chemical name</b>	Synthetic iron oxide			
<b>Delivery form</b>	Powder			
<b>Colour index</b>	Combination of Pigment red 101, yellow 42 and black 11			
<b>CAS No./EC No.</b>	1309-37-1, 51274-00-1, 1317-61-9/215-168-2,257-098-5,215-277-5			
<b>Specifications</b>	Contents	%	≥88	ISO1248
	Oil absorption	ml/100g	20~30	ISO787-5
	Res. on 325 mesh	%	≤0.3	ISO787-7
	Water soluble salts	%	≤0.5	ISO787-3
	Moisture	%	≤1.5	ISO787-2
	pH value		4~7	ISO787-9
	Ignition loss (1,000°C, ½ h)	%		DIN55913
	Bulk density	g/cm <sup>3</sup>	0.6~0.9	ISO787-11
	Specific gravity	g/cm <sup>3</sup>	4.8	ISO787-10
	Particle size BET	µm	Irregular	Electron Micrographs
	Dispersibility (Hegman)	µm		ISO787-20
	Tinting Strength (Compared with Standard)	%	95~105	ISO787-24
	Color Difference ΔE (Compared with Standard)		≤1.0	ISO787-1
<b>Sales packing</b>	In 25kg paper bag/1000kg bulk bag then palletized			
<b>Transport &amp; Storage</b>	Protect against weathering / Store in a dry place, temperatures of above 80 °C must be avoided			
<b>Safety</b>	The product is not classified as hazardous under EC 1907/2006 & EC 1272/2008			

Unit C, 11 Floor, Baima Mansion, Miduqiao Road, Hangzhou, 310005 China

Tel: +86 (571) 85 81 21 60 Fax: +86 (571) 85 81 21 61

E-mail: info@ironoxide.com.cn http://www.ironoxide.com.cn