

# Product Specification



Product code:

RK520

Product name:

Bronze satin

Particle size:

5-25  $\mu$  m

Composition	Content	CAS No.	EC No.	CI No.
Mica	55%-59%	12001-26-2	--	77019
Diiron Trioxide( $\text{Fe}_2\text{O}_3$ )	41%-45%	1309-37-1	215-168-2	77491

Test items	Product Information	Test method
Appearance	bronze, free flowing powder	RIKA In House Method
Odor	odorless	RIKA In House Method
Particle size	5-25 $\mu$ m (80% under this range)	Laser diffraction measurement
pH value	4-9(10% aqueous suspension)	ISO787-9
Loss on drying	$\leq$ 0.5% (105 $^{\circ}$ C)	ISO787-2
Oil absorption	50-70g/100g	ISO787-5
Density (20 $^{\circ}$ C)	2.8-3.4g/cm <sup>3</sup>	ISO787-10
Bulk density	15-40g/100ml	ISO60-2000

Heavy metal	Product Information	Test method
Lead (Pb.)	<10 ppm	ICP/ICP-MS
Antimony (Sb.)	<2 ppm	ICP/ICP-MS
Arsenic (As.)	<2 ppm	ICP/ICP-MS
Barium (Ba.)	<50 ppm	ICP/ICP-MS
Cadmium (Cd.)	<3 ppm	ICP/ICP-MS
Chrome (Cr.)	<100 ppm	ICP/ICP-MS
Mercury (Hg.)	<1 ppm	ICP/ICP-MS
Selenium (Se.)	<10 ppm	ICP/ICP-MS
Copper (Cu.)	<50 ppm	ICP/ICP-MS
Nickel (Ni.)	<10 ppm	ICP/ICP-MS
Zinc (Zn.)	<50 ppm	ICP/ICP-MS
Cobalt(Co.)	<30 ppm	ICP/ICP-MS

Date of issue:15/07/2017

Version:2.0/EN