

"MAGIC IN PAINTS"

SMK-6001

SEMKYD FA 50 W 60

DESCRIPTION

SMK-6001 is Special Fatty Acid based Medium Oil Alkyd Resin.

PRINCIPLE PROPERTIES

- ✓ Very good mechanical resistance
- ✓ Excellent hardness and flexibility
- ✓ Very good gloss and gloss retention
- ✓ High chemical and weathering resistance

RECOMENDED APPLICATIONS

- ✓ Anticorrosive paints
- ✓ Metal Surface
- ✓ Industrial varnishes and paints

SOLUBILITY

Solvent Type	Solubility
Toluene	+
Xylene	+
White Spirit	+
Buthanol	-
Methy-Ethyl Ketones	+
Glycol Ethers	+

COMPATIBILITY

Resin Type	Compatibility
Rosin Esters	-
Amino Resins	-
Short Oil Alkyds	+
Medium Oil Alkyds	+
Long Oil Alkyds	+
Aliphatic Hardeners	+
Aromatic Hardeners	+
Isocyanate Hardener	-
Polyether Polyol	-

TECHNICAL SPECIFICATIONS

Composition		
Oil type	Special Fatty Acid	
Oil Length, %	~50 %	
Solvent	White Spirit	
PA Content, %	%27	
Appearance	Clear	
Test	Range	Method
Non Volatile, %	60±2 %	ISO 3251
Viscosity (25°C) Pa.s.	6 - 10	ISO 3219
Acid Value (mgKOH/g)	10 max	ISO 2114
Colour (Gardner)	7 max	ISO 4630-2
Density (g/cm ³)	0,95±0,02	ISO 2811-1

PACKAGING AND DELIVERY FORM

Resin is supplied in steel drum with net content of 190 Kg per drum. For the other package condition, please contact with us.

RECOMMENDED DRIER COMBINATIONS

Cobalt	0.04 - 0.06 %
Zr	0.05 - 0.07 %
Calcium	0.08 - 0.10 %

- As metals in relation to 100% resin

STORAGE AND SHELF LIFE

Store in at temperatures between 5-30 °C, well-sealed packaging, dry and well-ventilated storage, should be avoided from direct sunlight.

Storage Shelf Life – 12 months from date of production.

MATERIAL SAFETY

Before handling the product , SDS of SMK-6001 should always be read and well understood.

Safety procedures should be followed.

This document is prepared by SEMKIM authorized person. To more information please visit www.semkim.com.tr