

"MAGIC IN PAINTS"

## SMK-7000

### SEMKYD FA 60 W 70

#### DESCRIPTION

SMK- 7000 is a Special Fatty Acid Based Long Oil Alkyd Resin.

#### PRINCIPLE PROPERTIES

- ✓ Very good brushability
- ✓ Excellent outdoor colour durability and gloss retention
- ✓ Very good yellowing resistance
- ✓ Good through drying and hardening

#### RECOMENDED APPLICATIONS

- ✓ Air drying all interior and exterior architectural finishes, primers and undercoats

#### SOLUBILITY

Solvent Type	Solubility
Toluene	+
Xylene	+
White Spirit	+
n-Buthanol	-
Methy-Ethyl Ketones	+
Glycol Ethers	+

#### COMPATIBILITY

Resin Type	Compatibility
Rosin Esters	-
Amino Resins	-
Short Oil Alkyds	-
Medium Oil Alkyds	+
Long Oil Alkyds	+
Aliphatic Hardeners	+
Aromatic Hardeners	+
Cellulosic Resin	-
Phenoic Resin	-

#### TECHNICAL SPECIFICATIONS

Composition		
Oil type	Special Fatty Acid	
Oil Length, %	~60%	
Solvent	White Spirit	
PA Content %	%25	
Appearance	Clear	
OH%	1,6	
Test	Range	Method
Non Volatile, %	70±2 %	ISO 3251
Viscosity (25°C/%60) Pa.s	4,5 - 8	ISO 3219
Acid Value (mgKOH/g)	10 max	ISO 2114
Colour (Gardner)	7 max	ISO 4630-2
Density (g/cm <sup>3</sup> )	0.96±0,02	ISO 2811-1

#### PACKAGING AND DELIVERY FORM

Resin is supplied in steel drum with net content of 190 Kg per drum. For the other package condition, please contact with us.

#### RECOMMENDED DRIER COMBINATIONS

Cobalt	0.04 - 0.06 %
Zr	0.05 - 0.07 %
Calcium	0.08 - 0.10 %

- As metals in relation to 100% resin

#### STORAGE AND SHELF LIFE

Store in at temperatures between 5-30 °C, well-sealed packaging, dry and well-ventilated storage, should be avoided from direct sunlight.

Storage Shelf Life – 12 months from date of production.

#### MATERIAL SAFETY

Before handling the product , SDS of **SMK-7000** should always be read and well understood. Safety procedures should be followed.

This document is prepared by SEMKIM authorized person. To more information please visit [www.semkim.com.tr](http://www.semkim.com.tr)