

Description

UHVO-23920 is a Bisphenol-A Epoxy Diacrylate for use in UV and EB curing applications.

Characteristics

- High reactivity
- Excellent hardness
- Good scratch resistance
- High chemical resistance
- No reactive diluent

Suggested Application

- Coatings
- Inks and Overprint Varnishes

Typical Properties

Acid value [mg KOH/g]	≤ 2
Appearance	clear liquid
Colour (Gardner)	≤ 2
Viscosity @ 40 °C, Physica, D = 5/s [Pa·s]	85 - 105

Storage

The resin should be stored in a cool, dry place and should not be exposed to direct sunlight. Typical storage temperatures should be between 15 - 30 °C. Do not store this product under an oxygen-free atmosphere, as the inhibitor requires oxygen to work.

Shelf Life

The product has a shelf life of at least 12 months from the date of manufacture.

Safety

When handling this product, please work according to the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Disclaimer

This product is currently in scale-up and samples are from pilot production. Listed values are subject to change.