

### Description

URPR-23207 is a Reactive Polyamide based on dimerized vegetable acid and amines for use as an epoxy curing agent.

### Characteristics

- Leads to tough but flexible coatings with excellent water and chemical resistances
- Provides good adhesion and mechanical properties

### Suggested Application

- Epoxy curing agent for various applications like marine coatings, flooring, adhesives, casting and potting

### Typical Properties

Amine value [mg KOH/g]	340 - 410
Appearance	clear liquid
Colour, Gardner	≤ 10
Viscosity @ 25 °C, Physica, D = 5/s [Pa·s]	20 - 30

### Storage

The product should be stored in a cool, dry place in unopened original packaging and should not be exposed to direct sunlight. Typical storage temperatures should be between 15 - 30 °C.

### Shelf Life

The product has a shelf life of at least 12 months from the date of manufacture.

### Safety

When handling this product, please work according to the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

### Packaging

180 kg drums.

### Disclaimer

This product is currently under development/in scale-up. Listed values are subject to change.